

Technical Specifications

<u>PROPERTY</u>	<u>TEST STANDARD</u>	<u>RESULTS</u>
Water Absorption and Bulk Specific Gravity	ASTM C97/C97M-18	Water Absorption: 0.02% Bulk Specific Gravity: 2.26
Compressive Strength	ASTM C170/C170M-17	Dry Condition: 238.1 MPa Wet Condition: 244.6 MPa
Flexural Strength	ASTM C880/C880M-15	Dry Condition: 58.8 MPa Wet Condition: 67.3 MPa
Impact Resistance	EN 14617-9:2005	11.86 J
MOH'S Hardness	EN 101	7
Abrasion Resistance	ASTM C241/C241M-15	39.6
Stain Resistance Test	ANSI Z124.6-2007 Section 5.2	Stain resistance rating: 50 The maximum stain depth: 0.057mm

