

Technical Specifications

<u>PROPERTY</u>	<u>TEST STANDARD</u>	<u>RESULTS</u>
Water Absorption	ASTM C97/C97M-15	0.04%
Apparent Density	ASTM C97/C97M-15	2397kg/m ³
Compressive Strength Wet Condition	ASTM C170/C170M- 15b	245 MPa
Compressive Strength Dry Condition	ASTM C170/C170M- 15b	252 MPa
Stain Resistance Test	ANSI Z 124.6- 2007	Total Stain Resistance Value: 41 Maximum Individual Depth of Staining: 0.02mm
Chemical Resistance	ANSI Z 124.6- 2007	Unaffected
MOH'S Hardness	EN 101	7

